

Superwool® Plus Blanket



MSDS Aus: Superwool Plus Blanket

© 2009 Morgan Thermal Ceramics, a business within the Morgan Ceramics Division of The Morgan Crucible Company plc



Description

Superwool® Plus™ blanket offers the same benefits as the other members of the Superwool fibre family but with improved handling strength and enhanced thermal properties. Superwool Plus blanket is manufactured from pure raw materials using a new manufacturing technology. In addition to enhanced thermal properties, large nuisance dust particles have been effectively eliminated making the product soft to the touch and less irritating during use.

Superwool Plus Blanket is made of long Superwool fibres having the same chemical formulation as the original and well proven Superwool 607® fibre product. It exhibits outstanding insulating properties at elevated temperatures and is available in a wide range of thicknesses and densities.

Superwool Plus blanket has excellent thermal stability and retains its original soft fibrous structure up to its maximum continuous use temperature. Superwool Plus blanket is needed from both sides and possesses high strength before and after heating. Superwool Plus blankets do not have binders or lubricants and will not emit any fumes or smell during the first firing. Superwool Plus blanket is flexible, easy to cut and shape and easy to install. (CAS number: 329211-92-9).

Classification Temperature 1200°C EN 1094-1

With Superwool Plus fibre, the consistent use of pure raw materials in all our factories globally has led to the 4% shrinkage temperature rising from >1100°C to >1200°C. For this reason, the classification temperature is now given as 1200°C in line with the EN 1094-1 norm.

Superwool Plus fibres have been proven over many years to withstand continuous use in an oxidising atmosphere at 1000°C. This temperature is quoted as the Maximum Continuous Use temperature.

For applications above 1000°C, Morgan Thermal Ceramics recommends Superwool® 607HT™ fibre which has a classification temperature of 1300°C.

Benefits

- Exceptional thermal insulation performance compared with industry standards
- Free of binder or lubricant
- Thermal stability
- Low heat storage
- Good resistance to tearing
- Flexible and resilient
- Immune to thermal shock
- Good sound absorption
- Exonerated from any carcinogenic classification under note Q of directive 97/69EC

SUPERWOOL® is a patented technology for high temperature insulation wools which have been developed to have a low bio persistence (information upon request). This product may be covered by one or more of the following patents, or their foreign equivalents: - SUPERWOOL® PLUS™ products are covered by patent numbers: - US5714421, US5994247, US6180546, US7259118, and EP0621858. SUPERWOOL® 607HT™ products are covered by patent numbers: - US5955389, US6180546, US7259118, US7470641, US7651965, US7875566, EP0710628, EP1544177, and EP1725503. A list of foreign patent numbers is available upon request to The Morgan Crucible Company plc.

Superwool® Plus Blanket



Main Properties

Classification temperature	°C	1200
Maximum continuous use temperature	°C	1000
Colour		White
Density	kg/m ³	64, 96, 128
Typical tensile strength of 128 kg/m ³ density (EN 1094-1)	kPa	75
High Temperature Performance Permanent linear shrinkage after 24 hours isothermal heating at 1200°C	%	<4 [typically <1]

Thermal Conductivity (ASTM C-201)

Mean Temp (°C)	64 kg/m ³	96 kg/m ³	128 kg/m ³
200	0.06	0.05	0.05
400	0.10	0.09	0.08
600	0.17	0.14	0.12
800	0.26	0.21	0.18
1000	0.38	0.29	0.25

Morgan Thermal Ceramics gives all Thermal Conductivity data according to the well established ASTM C-201 method

Chemical Composition (%)

SiO ₂	62-68
CaO	26-32
MgO	3-7
Other	>1

Availability and Packaging

Thickness mm	Density (kg/m ³)			Length mm
	64	96	128	
6			○	5500 x 4
10		○	○	18500
13		X	X	14640
25	X	X	X	7320
38	X	X	X	4880
50	○	X	X	3660

Standard width is 610mm wide. Marks (○) and width 1220mm available upon request (subject to minimum order requirements).

Typical Applications

- Power generation (HRSG duct insulation)
- Process heater linings
- Pipe wrap
- Furnace and kiln linings
- Storage heater insulation
- Domestic Oven insulation
- Automotive exhaust heat shields
- Aluminium transfer launder covers
- Welding stress relief

Frequency (Hz)	Sound Absorption Coefficient (SAC)							Sound Absorption Rating
	125	250	500	1000	2000	4000	Overall SAC	
Unfaced	0.15	0.75	1	1	1	0.75	1	Class A
Faced with glass cloth	0.4	0.95	0.95	0.85	0.8	0.65	0.8	Class B
Faced with 20µm reinforced aluminium foil	0.45	0.9	0.75	0.65	0.65	0.45	0.65	Class C

Morgan Thermal Ceramics
10 – 14 Toogood Avenue
Beverley SA 5009, Australia
P: +61 (8) 8243 5300
F +61 (8) 8243 0571

ISO 9001:2008



The values given herein are typical values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Therefore, the data contained herein should not be used for specification purposes. Check with your Thermal Ceramics office to obtain current information.